

## Q8 Brunel XF 711

*Exceptional performing extremely biostable water-soluble cutting fluid*

### Description

Q8 Brunel XF 711 is an advanced biostable soluble metalworking fluid incorporating the latest technology of high purity synthetic base fluids obtained chemically from natural gas in an unique combination with lubricity additives and selected key components to provide outstanding performance. Q8 Brunel XF 711 offers superior wetting and detergency characteristics, reducing fluid drag out and ensuring excellent machine cleanliness. Fluid consistency remains stable in either soft or hard make-up water.

### Applications

Q8 Brunel XF 711 is designed to excel on high speed machining applications on cast iron, carbon steel and ferrous metals in general. Due to its high detergency characteristics, it has a good fit in tube forming applications and welded tubes production. The versatile formulation is highly resistant to bacterial infection and significantly exceeds conventional fluid duration periods, providing noticeable cost and waste reductions. With limited maintenance required, Q8 Brunel XF 711 is ideally suited for centralised systems and single sump machines utilising 'lights-out' practices.

### User instructions

1. The correct mixing procedure is to add Q8 Brunel XF 711 to water and stir. For this operation we recommend positive displacement (Dosatron type) mixing units.
2. In order to preserve the integrity of this product drums should be stored inside a building (5-40 °C) protected from frost and direct sunlight.
3. Recommended concentrations are listed below.

General machining	4 – 6 %
Severe operations	8 – 12 %

Note: In some circumstances and applications, it is beneficial to exceed the recommendations shown above.

### Environment, Health and Safety

Q8 Brunel XF 711 has an advanced safety profile. It does not contain biocides and it is free of chlorine, cresols, nitrites, boron, boric acid, DCHA and secondary amines. It is compliant with the TRGS 611 specification. This ensures environmental safety & operator health. Also the reduced smell in the application improves operator environment. Please consult the Material Safety Data Sheet for instructions regarding safe handling and environmental issues.

### Properties

	Method	Unit	Typical
Base fluid content	-	%	8
Density, 20 °C	D 4052	g/ml	0.992
Appearance (Emulsion)	Visual	-	Traslucida
pH@3% in 400 ppm CaCO3 water	D 1287	pH	9.6
Determination of rust prevention characteristics of water-mix metalworking fluids	IP 287	%	3
Corrosion characteristics of water-mix metalworking fluids	IP 125	%	2
Refractometer Factor	-	-	2.4

The figures above are not a specification. They are typical figures obtained within production tolerances.

### Remarks

Please contact your Q8Oils representative for further advice and support on your specific application and equipment.

## Sustainability

The product Carbon Footprint (PCF), cradle-to-gate (Q8Oils state of the art facility in Belgium), of Q8 Brunel XF 711 is **0.83** kg CO<sub>2</sub>eq / kg.

Please contact Q8Oils to learn more about the positive environmental impact, the handprint, of this product.

For more info check here



**we  
take  
care**