

# Q8 Porta 105P

Process oil with optimum performance

### **Description**

Q8 Porta 105P is an advanced process oil with optimum performance and a high oxidation and thermal stability. This light coloured oil has a low aromatic and nitrogen content and minimum evaporation losses when heated. Q8 Porta 105P improves the elasticity of the rubber components.

# **Applications**

Q8 Porta 105P is used in rubber and ink industry. It is applied in softeners and extenders (rubber industry). Q8 Porta 105P is also recommended as anti-dust oil in the agriculture industry and carrier oil in the lubricants industry.

#### **Benefits**

- Reduction of product portfolio through extended lubricant applications
- Highly resistant to ageing
- Optimum thermal stability
- Low evaporation

# Specifications & Approvals

ISO 11158 HH ISO 6743-4 HH

# **Properties**

	Method	Unit	Typical
Viscosity Grade	-	-	105P
Density, 15 °C	D 4052	g/ml	0,882
Kinematic Viscosity, 40 °C	D 445	mm²/s	105.4
Kinematic Viscosity, 50 °C	D 445	mm²/s	61.1
Kinematic Viscosity, 100 °C	D 445	mm²/s	11.5
Viscosity Index	D 2270	-	95
Total Acid Number	D 974	mg KOH/g	<0.05
Pour Point	D 97	°C	-9
Flash Point, COC	D 92	°C	264
Flash Point, P-M	D 93	°C	255
Ash	D 482	% mass	<0.01
Sulfur	D 2622	% mass	0.78
Carbon Residue	D 524	% mass	0.09
Refractive Index n20/D	D 1218	-	1.485
Refractivity Intercept	D 2140	-	1.045
Hydrocarbons: Aromatic Rings	D 2140	%	4.1
Hydrocarbons: Naphthenic Rings	D 2140	%	29.4
Hydrocarbons: Paraffinic Chains	D 2140	%	66.4
Aniline Point	D 611	°C	112.9
Clay-gel adsorption: Aromatics	D 2007	% mass	29.7
Clay-gel adsorption: Asphaltenes	D 2007	% mass	<0.1
Clay-gel adsorption: Polar Compounds	D 2007	% mass	1.5
Clay-gel adsorption: Saturates	D 2007	% mass	68.8
DMSO extract	IP 346	%	<1

Mathad

Unit

Typical

The figures above are not a specification. They are typical figures obtained within production tolerances.

# Sustainability

The product Carbon Footprint (PCF), cradle-to-gate (Q80ils state of the art facility in Belgium), of Q8 Porta 105P is **1.22** kg  $CO_2$ eq / kg. Please contact Q80ils to learn more about the positive environmental impact, the

handprint, of this product. For more info check here

