

Q8 T 2500

Synthetic transmission and hydraulic oil for extreme working conditions

Description

Q8 T 2500 is a synthetic low viscosity transmission and hydraulic oil with outstanding anti-scuffing performance in the most extreme working conditions. It reduces wet brake noise and improves smooth braking thanks to its high temperature stability. Q8 T 2500 offers an excellent oxidation stability, outstanding lubricating properties and protects against rust and corrosion.

Applications

Q8 T 2500 is used for Volvo Construction Equipment requiring Volvo WB 102 fluid. It is used to lubricate transmissions, wet brake/clutch and hydraulic systems. This oil also meets the requirements of several other OEMs such as ZF.

Benefits

- Superb oxidation stability.
- Outstanding frictional properties for smooth brake operation.
- Outstanding viscosity retention providing highest gear protection.
- Limits wet brake noise while limiting friction plate wear.
- Excellent response of hydraulic components.

Specifications, recommendations and approvals

| API | GL-4 | Massey Ferguson | CMS M 1110 |
|------------------|------------|-----------------|----------------|
| Allison | C-4 | Massey Ferguson | CMS M 1127-B |
| Case | MS 1206 | Massey Ferguson | CMS M 1135 |
| Case | MS 1207 | Massey Ferguson | CMS M 1141 |
| Case | MS 1209 | Massey Ferguson | CMS M 1143 |
| Case | MS 1210 | Massey Ferguson | CMS M 1145 |
| Case New Holland | MAT 3505 | New Holland | NH 410-C |
| Case New Holland | MAT 3525 | Volvo | 97304 (WB 102) |
| Case New Holland | MAT 3526 | ZF | TE-ML 03E |
| Ford | M2C86-C | ZF | TE-ML 03F |
| John Deere | JDM J20D | ZF | TE-ML 05F |
| Kubota | Super UDT2 | ZF | TE-ML 06K |

Properties

| | Method | Unit | Typical | |
|------------------------------|----------|-------|---------|--|
| Viscosity Grade | SAE J306 | SAE | 70W-75 | |
| Density, 15 °C | D 4052 | g/ml | 0,859 | |
| Density, 20 °C | D 4052 | g/ml | 0,856 | |
| Kinematic Viscosity, 40 °C | D 445 | mm²/s | 39.5 | |
| Kinematic Viscosity, 100 °C | D 445 | mm²/s | 7.7 | |
| Viscosity Index | D 2270 | - | 181 | |
| Brookfield Viscosity, -40 °C | D 2983 | Pa.s | 18,5 | |
| Pour Point | D 97 | °C | -48 | |
| Flash Point, COC | D 92 | °C | 228 | |

The figures above are not a specification. They are typical figures obtained within production tolerances.

Remarks

Product Data Sheet includes a selection of specifications, for full overview please consult the Q80ils website.

Sustainability

The product Carbon Footprint (PCF), cradle-to-gate (Q8Oils state of the art facility in Belgium), of Q8 T 2500 is **1.36** kg CO_2eq / kg . Please contact Q8Oils to learn more about the positive environmental impact, the handprint, of this product. For more info check here

