Q8Oils

Q8 Holbein Bio Plus 46

Synthetic ester-based hydraulic fluid with high biodegradability.

Description

Q8 Holbein Bio Plus 46 is an outstanding synthetic hydraulic fluid based on unsaturated esters for year-round use in mobile and stationary hydraulic systems. Adapted for use in sensitive areas where high biodegradability is a requirement. Q8 Holbein Bio Plus 46 easily outperforms the ISO HEES specifications, meets the Swedish Standard environmental requirements SS 155434 and is listed on the Swedish RISE list.

Applications

Q8 Holbein Bio Plus 46 is perfect for rough hydraulic systems in environmentally sensitive areas such as agriculture, forestry, water works and marine.

Benefits

- Readily biodegradable
- Eco-friendly and limited impact on the environment
- Free of harmfull components
- Does not contain zinc

Specifications & Approvals

| Bosch Rexroth | RE 90221 notes | Swedish Standard | SS 155434 BBV 46 Environmentally acceptable |
|---------------|----------------|------------------|--|
| ISO | 15380 HEES | | |

Properties

| | Method | Unit | Typical |
|------------------------------------|------------|------------|--------------|
| ISO Viscosity Grade | - | - | 46 |
| Colour | D 1500 | - | 1.5 |
| Density, 15 °C | D 4052 | g/ml | 906 |
| Kin. Viscosity Base Oil at 40 °C | D 445 | mm²/s | 48 |
| Kin. Viscosity Base Oil at 100 °C | D 445 | mm²/s | 9.5 |
| Viscosity Index | D 2270 | - | 185 |
| Flash Point, COC | D 92 | °C | 246 |
| Pour Point | D 97 | °C | -54 |
| Emulsion, Distilled Water, 54.4 °C | D 1401 | - | 40/40/0 (20) |
| Foam, 10 min settling, seq. 1-2-3 | D 892 | ml | 5/5/5 |
| Foam, 5 min blowing, seq. 1-2-3 | D 892 | ml | 0/0/0 |
| Rust Test, Proc. A and B, 24 h | D 665 | - | pass |
| Copper Strip, 3 h, 100 °C | D 130 | - | 1 |
| Biodegradability, 28 days | 0ECD 301 B | % | 77 |
| FZG Test, A/8.3/90 | DIN 51354 | load stage | 11 |

The figures above are not a specification. They are typical figures obtained within production tolerances.