

# Q8 Porta 19P

Process oil with optimum performance

### **Description**

Q8 Porta 19P is an advanced process oil with optimum performance and a high oxidation and thermal stability. This light coloured oil has a low aromatic and nitrogen content and minimum evaporation losses when heated. Q8 Porta 19P improves the elasticity of the rubber components.

# **Applications**

Q8 Porta 19P is used in rubber and ink industry. It is applied in softeners and extenders (rubber industry). Q8 Porta 19P is also recommended as anti-dust oil in the agriculture industry and carrier oil in the lubricants industry.

#### **Benefits**

- Reduction of product portfolio through extended lubricant applications
- Highly resistant to ageing
- · Optimum thermal stability
- Low evaporation

# Specifications & Approvals

**ISO** 11158 HH **ISO** 6743-4 HH

# **Properties**

	Method	Unit	Typical
Viscosity Grade	-	-	19P
Density, 15 °C	D 4052	g/ml	0,868
Kinematic Viscosity, 40 °C	D 445	mm²/s	20.22
Kinematic Viscosity, 50 °C	D 445	mm²/s	14.1
Kinematic Viscosity, 100 °C	D 445	mm²/s	4
Viscosity Index	D 2270	-	89
Total Acid Number	D 974	mg KOH/g	<0.05
Pour Point	D 97	°C	-24
Flash Point, COC	D 92	°C	190
Flash Point, P-M	D 93	°C	188
Ash	D 482	% mass	<0.01
Sulfur	D 2622	% mass	0.41
Carbon Residue	D 524	% mass	0.02
DMSO extract	IP 346	%	<1
Hydrocarbons: Aromatic Rings	D 2140	%	2.8
Hydrocarbons: Naphthenic Rings	D 2140	%	36.2
Hydrocarbons: Paraffinic Chains	D 2140	%	61.1
Refractive Index n20/D	D 1218	-	1.476
Refractivity Intercept	D 2140	-	1.044
Aniline Point	D 611	°C	97
Clay-gel adsorption: Aromatics	D 2007	% mass	17.4
Clay-gel adsorption: Asphaltenes	D 2007	% mass	<0.1
Clay-gel adsorption: Polar Compounds	D 2007	% mass	0.6
Clay-gel adsorption: Saturates	D 2007	% mass	82.1

Mathad

Unit

Typical

The figures above are not a specification. They are typical figures obtained within production tolerances.

# Sustainability

The product Carbon Footprint (PCF), cradle-to-gate (Q80ils state of the art facility in Belgium), of Q8 Porta 19P is  $\bf 1.21~kg~CO_2eq/kg$ . Please contact Q80ils to learn more about the positive environmental impact, the

handprint, of this product. For more info check here

